



Offset printing paper

Ref.: 7054 - MP

Origin: Slovakia

			70	80	90	100	110	120
Grammage	g/m ²	ISO 536	70 ± 2.5	80 ± 3.0	90 ± 3.0	100 ± 4.0	110 ± 4.0	120 ± 4.5
Caliper	mm/1000	ISO 534	90 ± 4	103 ± 4	116 ± 4	126 ± 5	137 ± 5	144 ± 6
Roughness Bendtsen	ml/min	ISO 8791-2	225 ± 75	225 ± 75	225 ± 75	225 ± 75	225 ± 75	225 ± 75
Opacity	%	ISO 2471	min 89.0	min 91.0	min 92.0	min 93.0		
Moisture	%	ISO 287	6.2 ± 0.7	6.2 ± 0.7	6.2 ± 0.7	6.2 ± 0.7	6.2 ± 0.7	6.2 ± 0.7
Brightness with UV	D65 %	ISO 2470	103.5 ± 1.5	103.5 ± 1.5	103.5 ± 1.5	103.5 ± 1.5	103.5 ± 1.5	103.5 ± 1.5
CIE Whiteness		ISO 11475	145 ± 3.0	145 ± 3.0	145 ± 3.0	145 ± 3.0	145 ± 3.0	145 ± 3.0

			140	170	180	190	220	250	300
Grammage	g/m ²	ISO 536	140 ± 5.5	170 ± 7.0	180 ± 7.0	190 ± 7.0	220 ± 8.0	250 ± 8.0	300 ± 10.0
Caliper	mm/1000	ISO 534	164 ± 6	198 ± 7	209 ± 7	221 ± 7	256 ± 8	285 ± 9	346 ± 10
Roughness Bendtsen	ml/min	ISO 8791-2	225 ± 75	225 ± 75	225 ± 75	225 ± 75	225 ± 75	225 ± 75	225 ± 75
Opacity	%	ISO 2471							
Moisture	%	ISO 287	6.2 ± 0.7	6.2 ± 0.7	6.2 ± 0.7	6.2 ± 0.7	6.2 ± 0.7	6.2 ± 0.7	6.2 ± 0.7
Brightness with UV	D65 %	ISO 2470	103.5 ± 1.5	103.5 ± 1.5	103.5 ± 1.5	103.5 ± 1.5	103.5 ± 1.5	103.5 ± 1.5	103.5 ± 1.5
CIE Whiteness		ISO 11475	145 ± 3.0	145 ± 3.0	145 ± 3.0	145 ± 3.0	145 ± 3.0	145 ± 3.0	145 ± 3.0

Product meets DIN 19306-2, Printing paper-Part 2: Technical delivery specifications for offset paper, coated and uncoated, white and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001, 14001 and 18001.

Offset printing paper

Ref.: 3504

Origin: Russia

GRAMMAGE		gsm	ISO 536	70	± 2.5
CALIPER		mm/1000	ISO 534	91	± 4
BREAKING LENGTH	MD	m	ISO 1924-2	min 4500	
	CD	m			
ROUGHNESS BENDTSEN		ml/min	ISO 8791-2	220	± 100
CIE WHITENESS			ISO 11475	145	± 3
BRIGHTNESS WITH UV		%	ISO 2470	103.5	± 1.5
OPACITY		%	ISO 2471	min 85	